

POR 304/CM-HD

COMPOSIZIONE	EPDM (no zolfo)
NORMA RIFERIMENTO ASTM D-1056	RE 42 / 2A2
STRUTTURA CELLULARE	CHIUSE
COLORE	NERO
DENSITA' (ISO 845-88 - ASTM D 3575)	160 +/-20 KG/m3
ASSORBIMENTO ACQUA (ASTM D 1056)	2 % < 5%
CAMPO DI TEMPERATURA	- 40° C + 95° C
RESTRINGIMENTO LINEARE DOPO 22h A 70 °C	< 5%
ALLUNGAMENTO A ROTTURA - (ASTM D 412)	> 150%
RESISTENZA A ROTTURA - (ASTM D 412)	5,5 KG/cmq (550 kPa)
RESISTENZA A LACERAZIONE - (ASTM D 624)	3,5 KG/cm (0,35 kN/m)
RESISTENZE	AIR+ U.V. OTTIME OZONO 48H/ 200 pphm
RESISTENZA ALLA COMPRESSIONE - (ASTM 1056/85)	AL 25% - 0,56 KG/cmq (56 kPa) AL 50% - 1KG/cmq (100 kPa)
FORZA ALLA COMPRESSIONE (TSM 1501 G - 2A2)	57 KpA
FORZA ALLA DEFORORMAZIONE IN COMPRESSIONE DEL 40% (Norma VW TL 520.65)	N/cm2 10,8
COMPRESSION SET 50% 22 h. - (ASTM 1056/85)	25%
DUREZZA SHORE 00 - (ASTM D 2240)	50/60
RESISTENZA AL FUOCO - (MVSS 302 - FIAT 50433)	PASSA (FR)
RESISTENZA AL FUOCO - (UL 94)	HBF
VULCANIZZATO PEROSSIDICO	NO ZOLFO

Le infor.sopra citate devono essere considerate come una guida,ma non possono essere citate come un obbligo da parte ns.

POR 304/CM-HD

BASIS	EPDM (no sulphur)
REFERRING STANDARD NORM ASTM D-1056	RE 42 / 2A2
CELLULAR STRUCTURE	CLOSED
COLOUR	BLACK
DENSITY (ISO 845-88 - ASTM D 3575)	160 +/-20 KG/m3
WATER ABSORPTION (ASTM D 1056)	2 % < 5%
TEMPERATURE RANGE	- 40° C + 95° C
LINEAR SHRINKAGE AFTER 22h at 70°C	< 5%
ULTIMATE ELONGATION - (ASTM D 412)	> 150%
TENSILE STRENGTH - (ASTM D 412)	5,5 KG/cmq (550 kPa)
TEAR RESISTANCE - (ASTM D 624)	3,5 KG/cm (0,35 kN/m)
RESISTENCE	AIR+ U.V. VERY GOOD OZONE 48H/ 200 pphm
COMPRESSION STRENGTH - (ASTM 1056/85)	At 25% - 0,56 KG/cmq (56 kPa) At 50% - 1KG/cmq (100kPa)
COMPRESSION STRENGTH - (TSM 1501 G - 2A2)	57 KpA
COMPRESSION STRENGTH TO DEFLECTION AT 40% (Norm VW TL 520.65)	N/cm2 10,8
COMPRESSION SET 50% 22 h. - (ASTM 1056/85)	25%
SHORE HARDNESS 00 - (ASTM D 2240)	50/60
FIRE RESISTANT - (MVSS 302 - FIAT 50433)	PASS (FR)
FIRE RESISTANT - (UL 94)	HBF
PEROXIDE CURE	NO SULPHUR

The above given information should be considered as a guide but cannot regarded as an engagement from our side.