



To

EUROFOAM S.r.l.

Via C. Colombo, 12

20020 Lainate (MI)

Date, March 14<sup>th</sup> 2019  
TR n° **163-(eng)/2019**  
Ref. Our Offer n.251 dated 25.02.2019

Received 08.03.2019 Start tests 11.03.2019 End tests 14.03.2019 Page 1 of 1

---

## T E S T R E P O R T

---

**Subject:** DETERMINATION OF FLAMMABILITY ACCORDING TO FMV SS 302, ON A POLIMERIC FOAM MARKED "**POR 304/B-OPC**"

**Sample :**

**POR 304/B-OPC**

Test method

FLAMMABILITY

mm/min

125

FMVSS 302:2011

The sampling has been carried out by the Customer.  
----

The contained results refer only to the tested sample.  
----

This report cannot be partially reproduced without the laboratory approval.

L. Lamboglia, *Operator*



F. Negrone, *Director*





Spettabile

EUROFOAM S.r.l.

Data, 14 Marzo 2019

RP n° **163/2019**

Rif. Ns. Offerta n.251 del 25.02.2019

Via C. Colombo, 12

20020 Lainate (MI)

Camp. ricevuto il 08.03.2019 Data inizio prove: 14.03.2019 Data fine prove: 14.03.2019 Pag. 1 di 1

---

**R A P P O R T O                      D I                      P R O V A**

---

**Oggetto:** PROVE DI INFIAMMABILITA' SU DI UN MATERIALE ESPANSO DENOMINATO "POR 304/B-OPC" FORNITO DAL COMMITTENTE SOTTO FORMA DI LASTRE VULCANIZZATE A SPESSORE mm 4.

<u>Campione</u>		<u>POR 304/B-OPC</u>	<u>Metodo di Prova</u>
<u>Velocità di combustione</u>	mm/min	125	FMVSS 302:2011

Il campionamento è stato eseguito a cura del Committente.

----

I risultati ottenuti si riferiscono esclusivamente al campione provato.


----

Il presente rapporto di prova non può essere riprodotto parzialmente salvo approvazione del Laboratorio.

L' OPERATORE

  
L. Lamboglia

IL DIRETTORE

  
F. Negroni  
